

# Guide to Whitford Xylan® Flexible Finishes for Automotive Applications

Product	Solvent-borne	Water-borne	D.F.T.	No. of Components	Cure Temp. (PMT)	Working Temp.	Colours	Comments/Uses
2020/G1453		•	10µ - 15µ	1	120°C/10 mins.	-40 to 100°C	Black	Low cure, high performance, antisqueak, weatherstrip coating
2020/G1470		•	10µ - 15µ	1	205°C/5 mins.	-40 to 100°C	Black	High performance, antisqueak weatherstrip coating
2020/G2922		•	10µ - 15µ	1	180°C/5 mins.	-40 to 100°C	Black	High performance, weatherstrip coating
2022-A-G1443 / 2022-B-G1448		•	15µ - 25µ	2	150°C/5 mins.	-40 to 100°C	Black	Two component, high performance, antisqueak weatherstrip coating
2022-A-G1485 / 2022-B-G1448		•	15µ - 25µ	2	120°C/5 mins.	-40 to 100°C	Black	Two component, high performance, antisqueak matt weatherstrip coating
2121-A-G0742 / 2121-B-G1462		•	25µ - 35µ	2	150°C/5 mins.	-40 to 100°C	Black	High performance glass-run coating
2222/D8001		•	12µ - 18µ	1	120°C/10 mins.	-40 to 100°C	Black	Weather resistant appearance coating for interior applications
2222/G1660		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Silver Shadow	Metallic-effect interior coloured coating
2222/G1661		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Silver Starlight	Metallic-effect interior coloured coating
2222/G1662		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Steel	Metallic-effect interior coloured coating
2222/G1663		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Platinum	Metallic-effect interior coloured coating
2222/G2101		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Bronze	Pearlescent interior coloured coating
2222/G2102		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Copper	Pearlescent interior coloured coating
2222/G2103		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Silver/Copper	Pearlescent interior coloured coating
2222/G2104		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Viola Blue	Pearlescent interior coloured coating
2222/G2105		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Phthalo Blue	Pearlescent interior coloured coating
2222/G2106		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Silver	Pearlescent interior coloured coating
2222/G2115		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Red	Pearlescent interior coloured coating
2222/G2116		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Dark Red	Pearlescent interior coloured coating
2222/G2117		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Green	Pearlescent interior coloured coating

**Whitford Worldwide**

[www.whitfordww.com](http://www.whitfordww.com)

For more information, consult the Product Data Sheets or website, or contact your nearest Whitford representative at the addresses overleaf.

# Guide to Whitford Xylan® Flexible Finishes for Automotive Applications

Product	Solvent-borne	Water-borne	D.F.T.	No. of Components	Cure Temp. (PMT)	Working Temp.	Colours	Comments/Uses
2222/G2118		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Dark Green	Pearlescent interior coloured coating
2222/G2119		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Tan	Pearlescent interior coloured coating
2222/G2120		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Arctic Fire	Pearlescent interior coloured coating
2230/G0545		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Grey	Interior "Soft-Touch" coating
2230/G0564		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Dark Blue	Interior "Soft-Touch" coating
2230/G0565		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Beige	Interior "Soft-Touch" coating
2230/G0566		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Matt Black	Interior "Soft-Touch" coating
2320-A-G2945 / 2320-B-G2946	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Black	Weatherstrip coating
2321-A-G0778 / 2321-B-G0779	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Black	Glass-run coating
2322-A-G1455 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Dark Red	Coloured appearance coating
2322-A-G1456 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Dark Emerald Green	Coloured appearance coating
2322-A-G1457 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Basalt Grey	Coloured appearance coating
2322-A-G1458 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Anthracite	Coloured appearance coating
2322-A-G1459 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Dark Pearl	Coloured appearance coating
2525/D6135		•	10µ - 15µ	1	Not Applicable	-40 to 100°C	Black	UV Cure weatherstrip coating
4016/F1587	•		2µ - 5µ	1	Not Applicable	-40 to 100°C	Opaque	Primer for solvent-borne coatings
4016/F9160	•		2µ - 5µ	1	Not Applicable	-40 to 100°C	Clear	High performance primer for waterborne and solvent-borne coatings
4020/G0523		•	2µ - 5µ	1	Apply on Warm Substrate	-40 to 100°C	Opaque	Primer for waterborne coatings

## Whitford Worldwide

[www.whitfordww.com](http://www.whitfordww.com)

For more information, consult the Product Data Sheets or website, or contact your nearest Whitford representative at the addresses below.

**Europe:** Whitford Plastics Ltd  
Christleton Court, Manor Park,  
Runcorn, Cheshire WA7 1ST, UK  
Tel: +44 (\*)1928 571000  
Fax: +44 (\*)1928 571010  
Email: [sales@whitfordww.co.uk](mailto:sales@whitfordww.co.uk)

**Asia-Pacific:** Whitford Ltd  
22<sup>nd</sup> Floor, Oterprise Square  
26 Nathan Road, Kowloon, Hong Kong  
Tel: +852 2559 3833  
Fax: +852 2857 7911  
Email: [sales@whitfordww.com.hk](mailto:sales@whitfordww.com.hk)

**South America:** Whitford Comm. e Ind. Ltda.  
Avenida Sao Carlos 620,  
Distrito Industrial Américo Brasiliense,  
Sao Paulo 14820-000, Brazil  
Tel: +55 16 3392 6885, Fax: +55 16 3392 6646  
Email: [sales@whitfordww.com.br](mailto:sales@whitfordww.com.br)

**North America:** Whitford Corporation  
33, Sproul Road, Frazer PA 19380  
Tel: +1 610 2963200  
Fax: +1 610 6474849  
Email: [sales@whitfordww.com](mailto:sales@whitfordww.com)