

Guide to Whitford Xylan® Flexible Finishes for Automotive Applications

Product	Solvent-borne	Water-borne	D.F.T.	No. of Components	Cure Temp. (PMT)	Working Temp.	Colours	Comments/Uses
2020/G1453		•	10µ - 15µ	1	120°C/10 mins.	-40 to 100°C	Black	Low cure, high performance, antisqueak, weatherstrip coating
2020/G1470		•	10µ - 15µ	1	205°C/5 mins.	-40 to 100°C	Black	High performance, antisqueak weatherstrip coating
2020/G2922		•	10µ - 15µ	1	180°C/5 mins.	-40 to 100°C	Black	High performance, weatherstrip coating
2022-A-G1443 / 2022-B-G1448		•	15µ - 25µ	2	150°C/5 mins.	-40 to 100°C	Black	Two component, high performance, antisqueak weatherstrip coating
2022-A-G1485 / 2022-B-G1448		•	15µ - 25µ	2	120°C/5 mins.	-40 to 100°C	Black	Two component, high performance, antisqueak matt weatherstrip coating
2121-A-G0742 / 2121-B-G1462		•	25µ - 35µ	2	150°C/5 mins.	-40 to 100°C	Black	High performance glass-run coating
2222/D8001		•	12µ - 18µ	1	120°C/10 mins.	-40 to 100°C	Black	Weather resistant appearance coating for interior applications
2222/G1660		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Silver Shadow	Metallic-effect interior coloured coating
2222/G1661		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Silver Starlight	Metallic-effect interior coloured coating
2222/G1662		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Steel	Metallic-effect interior coloured coating
2222/G1663		•	15µ - 25µ	1	150°C/10 mins.	-40 to 100°C	Platinum	Metallic-effect interior coloured coating
2222/G2101		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Bronze	Pearlescent interior coloured coating
2222/G2102		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Copper	Pearlescent interior coloured coating
2222/G2103		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Silver/Copper	Pearlescent interior coloured coating
2222/G2104		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Viola Blue	Pearlescent interior coloured coating
2222/G2105		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Phthalo Blue	Pearlescent interior coloured coating
2222/G2106		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Silver	Pearlescent interior coloured coating
2222/G2115		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Red	Pearlescent interior coloured coating
2222/G2116		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Dark Red	Pearlescent interior coloured coating
2222/G2117		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Green	Pearlescent interior coloured coating

Whitford Worldwide

www.whitfordww.com

For more information, consult the Product Data Sheets or website, or contact your nearest Whitford representative at the addresses overleaf.

Guide to Whitford Xylan® Flexible Finishes for Automotive Applications

Product	Solvent-borne	Water-borne	D.F.T.	No. of Components	Cure Temp. (PMT)	Working Temp.	Colours	Comments/Uses
2222/G2118		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Dark Green	Pearlescent interior coloured coating
2222/G2119		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Pearl Tan	Pearlescent interior coloured coating
2222/G2120		•	12µ - 18µ	1	150°C/10 mins.	-40 to 100°C	Arctic Fire	Pearlescent interior coloured coating
2230/G0545		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Grey	Interior "Soft-Touch" coating
2230/G0564		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Dark Blue	Interior "Soft-Touch" coating
2230/G0565		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Beige	Interior "Soft-Touch" coating
2230/G0566		•	15µ - 25µ	1	120°C/5 mins.	-40 to 100°C	Matt Black	Interior "Soft-Touch" coating
2320-A-G2945 / 2320-B-G2946	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Black	Weatherstrip coating
2321-A-G0778 / 2321-B-G0779	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Black	Glass-run coating
2322-A-G1455 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Dark Red	Coloured appearance coating
2322-A-G1456 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Dark Emerald Green	Coloured appearance coating
2322-A-G1457 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Basalt Grey	Coloured appearance coating
2322-A-G1458 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Anthracite	Coloured appearance coating
2322-A-G1459 / 2322-B-G1460	•		15µ - 25µ	2	150°C/15 mins.	-40 to 150°C	Dark Pearl	Coloured appearance coating
2525/D6135		•	10µ - 15µ	1	Not Applicable	-40 to 100°C	Black	UV Cure weatherstrip coating
4016/F1587	•		2µ - 5µ	1	Not Applicable	-40 to 100°C	Opaque	Primer for solvent-borne coatings
4016/F9160	•		2µ - 5µ	1	Not Applicable	-40 to 100°C	Clear	High performance primer for waterborne and solvent-borne coatings
4020/G0523		•	2µ - 5µ	1	Apply on Warm Substrate	-40 to 100°C	Opaque	Primer for waterborne coatings

Whitford Worldwide

www.whitfordww.com

For more information, consult the Product Data Sheets or website, or contact your nearest Whitford representative at the addresses below.

Europe: Whitford Plastics Ltd
Christleton Court, Manor Park,
Runcorn, Cheshire WA7 1ST, UK
Tel: +44 (*)1928 571000
Fax: +44 (*)1928 571010
Email: sales@whitfordww.co.uk

Asia-Pacific: Whitford Ltd
22nd Floor, Oterprise Square
26 Nathan Road, Kowloon, Hong Kong
Tel: +852 2559 3833
Fax: +852 2857 7911
Email: sales@whitfordww.com.hk

South America: Whitford Comm. e Ind. Ltda.
Avenida Sao Carlos 620,
Distrito Industrial Américo Brasiliense,
Sao Paulo 14820-000, Brazil
Tel: +55 16 3392 6885, Fax: +55 16 3392 6646
Email: sales@whitfordww.com.br

North America: Whitford Corporation
33, Sproul Road, Frazer PA 19380
Tel: +1 610 2963200
Fax: +1 610 6474849
Email: sales@whitfordww.com